



(19)

Generated Document.

(11) Publication number: **07249618 A****PATENT ABSTRACTS OF JAPAN**(21) Application number: **06042182**(51) Int. Cl.: **H01L 21/31 H01L 21/318**(22) Application date: **14.03.94**

(30) Priority:

(43) Date of application publication: **26.09.95**

(84) Designated contracting states:

(71) Applicant: **FUJITSU LTD****FUJITSU VLSI LTD**(72) Inventor: **KURAMAE MASAKI**

(74) Representative:

**(54) MANUFACTURE OF SEMICONDUCTOR DEVICE**


(57) Abstract:

**PURPOSE:** To provide a forming method of a silicon nitride film wherein the improvement of oxidation resistance and high speed of film formation are compatible with each other.

**CONSTITUTION:** A silicon nitride film is formed by a thermal CVD method using silane and ammonia as material gas, at a temperature lower

than or equal to 630°C and a pressure higher than or equal to 10 Torr. In this case, higher order silane such as disilane and trisilane may be used instead of silane as the material gas, and hydrazine or derivative of hydrazine such as monomethylhydrazine and trimethylhydrazine may be used instead of ammonia as the material gas.

COPYRIGHT: (C)1995, JPO





07249618 A

PAGE 4 OF 4

<http://www.delphion.com/cgi-bin/viewpat.cmd/JP07249618A2>

5/10/01